

PRODUCT SPECIFICATION SHEET

	DATA		RESULTS	UNITS	TEST METHOD
PHYSICAL PROPERTIES	Tensile	MD TD	10,344 6,619	Psi Psi	ASTM D882 ASTM D882
	Elongation	MD TD	268 589	% %	ASTM D882 ASTM D882
	Elmendorf Tear	MD TD	4.7 66	Grams Grams	ASTM D1922 ASTM D1922
	Impact Strength		0.50	Ft/lbs.	ASTM D4272
	Puncture		1.85	Lbs.	FTMS 101C