



FICHE TECHNIQUE

Référence : EPM30B

Désignation : Étiquette pré découpée

PRODUCT DATA SHEET for EPM

PRODUCT DESCRIPTION: Flexible Magnetic with white pvc film

STANDARD THICKNESS: 0.9 mm(+/-0.03mm)

STANDARD WIDTH: depending on article number see below (+/- 0.1 mm)

STANDARD LENGTH: depending on article number see below (+/- 0.1 mm)

MAGNETIC PROPERTIES

Maximum Energy Product: 0.45 – 0.55 MGOe

Remanence: 1600 – 1900 G

Coercivity: 1200 – 1500 Oe

Intrinsic coercivity: 2200 – 2500 Oe

Pole width: 2.0 mm

Magnetic pull: 36 g/cm²

PHYSICAL PROPERTIES

Flexibility: can be wrapped around a rod with a 12mm radius at 20°C without cracking

Specific Gravity: 3.5 to 3.7 g/cm³

Cutting: Scissor cutting, knife-cutting, die-cutting and slitting can be done with ease

TEMPERATURE RESISTANCE

End-use temperature range: -30°C / +55°C

Short term resistance: + 65°C

MATERIAL PROPERTIES

The magnetic sheeting has a UV hardened coating on the magnetic side

PVC FILM

Outdoor Applications: 2-year durability under Middle European exposure conditions. Exposure to severe humidity, ultra-violet light or conditions found in tropical, subtropical or desert regions will cause a more rapid deterioration.

Printability:

Screen Printing: Solvent-based Inks	Yes
-------------------------------------	-----



RAJA

16, rue de l'étang • Paris Nord 2 • 95977 ROISSY CDG Cedex

Services commerciaux : tél. 3912* ou 0820 306 306* du lundi au vendredi de 8h à 18h30 - fax 0820 306 307* - www.raja.fr - Vos commandes 24h/24, 7 jours/7

Services administratifs : tél. 01 48 17 30 00 du lundi au vendredi de 8h30 à 18h30 - fax 01 48 17 30 30

* 0.099 € HT/mm

RAJA S.A. au capital de 10 000 000 € RCS Bobigny B 937080414

Screen Printing: UV Cure Inks	Yes
Conventional Offset Printing	Yes

Storage:

The material should be stored horizontally. Avoid sunlight and keep temperature between 10 and 30 degrees Celcius.

Notes:

1. Thickness of PVC film is 0.10mm.
2. Screen Printability with UV cure inks deteriorates with time. We strongly recommend users to use the product within 6 months after date of production when screen print with UV inks is involved in the application.

EPM:

EPM20B	Formats isotropic 20 x 100 mm with white vinyl, packed per 50 pieces in polybag with label (overall thickness: 0.9 mm)
EPM25B	Formats isotropic 25 x 80 mm with white vinyl, packed per 50 pieces in polybag with label (overall thickness: 0.9 mm)
EPM30B	Formats isotropic 30 x 100 mm with white vinyl, packed per 50 pieces in polybag with label (overall thickness: 0.9 mm)
EPM40B	Formats isotropic 40 x 120 mm with white vinyl, packed per 50 pieces in polybag with label (overall thickness: 0.9 mm)
EPM50B	Formats isotropic 50 x 150 mm with white vinyl, packed per 50 pieces in polybag with label (overall thickness: 0.9 mm)



RAJA

16, rue de l'étang • Paris Nord 2 • 95977 ROISSY CDG Cedex

Services commerciaux : tél. 3912* ou 0820 306 306* du lundi au vendredi de 8h à 18h30 - fax 0820 306 307* - www.raja.fr - Vos commandes 24h/24, 7 jours/7

Services administratifs : tél. 01 48 17 30 00 du lundi au vendredi de 8h30 à 18h30 - fax 01 48 17 30 30

* 0,99 € HT/mm

RAJA S.A. au capital de 10 000 000 € RCS Bobigny B 937080414