

FICHE TECHNIQUE

Référence : FED24

Désignation : Pack film étirable haute résistance (bobine de film + dérouleur acier)

Bobine de film

	Tolerance	Method
Film Width	Nominal 450mm +/- 1%	In house method
Roll Length	Nominal 300m +/- 5%	
Individual Roll Weight	Nominal 2.112kg +/-7.5% +core 0.2kg	
Spot Thickness	Nominal 17mu +/-20%	
Average Thickness	Nominal 17mu +/- 7.5%	
Dart Impact Strength	Not less than 65g	
Cling	Pass	
Roll Profile	Flush edge	
Opacity	Transparent	
Core	470x50mm	
Product composition	A blend of LLDPE (Linear low density polyethylene) & LDPE (Low density polyethylene)	
Storage	The product should be stored in a dry place not in direct sunlight at a temperature not greater than 25°C and not less than 10°C to maintain stability.	
Guarantee	This product is fit for its intended use for 3 months from the date of dispatch and therefore Total Polyfilm Limited is not able to accept any claims after this date.	


Purchaser remains responsible for determining whether the use complies with all relevant regulations.

This product is classed as tertiary packaging and is not suitable for direct food contact.


Dérouleur acier



SR
Dispenser manuale in metallo per film estensibile
Metal Stretch Film Dispenser
Dividire en métal pour Film extensible
Hand-Streichgerät aus Metall
Dispenser manuel en métal pour pellicule extensible



DS-7
Dispenser manuale rinforzato per film estensibile
Heavy Duty metal stretch film dispenser
Dividit en metal robuste pour film extensible
Hand-Stretchgerät aus Metall Schwerlast
Dispenser manual de alta resistencia por película extensible



SP38 - SP50
Dispenser manual in plasticop film extensibil
Plastic Stretch-Film Dispenser
Divisor en plasticop pour Film extensible
Hand-Stretchgerät aus Plastik
Dispenser manual en plástico por película extensible



ISP30 - ISP50
Impugnatura - Handle - Poignée - Griffe - Empuñadura

[illegible]

Type Type Type Type Type	Press (g) Weight (g) Pallet (g) Capacity (g) Press (g)	TWT		N°	Pressing Weight (g) Press (g) Capacity (g) Press (kg)	C/T			N° per box N° per box
						A	B	C	
DR	1130	74-60-34	000	8	9,530	17	29	22	216
SP1	2,380	76-58-38	500	8	11	23	32	25,6	72
SP50	290	56	500	32	8	54	38	30	512
SP28	219	56	500	32	7	54	38	30	512
SP76	199	66	150	32	3,590	26	33	23	512
SP56	199	56	150	32	3,590	26	33	23	512