



SCHEDA TECNICA - TECHNICHER DATENBLATT DATA SHEET - FICHE TECHNIQUE	DATA : 19/03/13
--	-----------------

RAJA
FILM ESTENSIBILE RIBOBINATO 300 m

TIPO :	EST/PSE	SPESSORE :	0,017 mm	FASCIA :	450 mm
--------	---------	------------	----------	----------	--------

CARATTERISTICA , PROPERTY		Unità	Metodo	Valore	Toll.
SPESSORE , DICKE GAUGE , EPAISSEUR		mm		0,017	+/-10%
CARICO ELASTICO , STRECKSPANNUNG YIELD STRESS , CHARGE ELASTIQUE	L MD	$\frac{N}{mm^2}$	ASTM D 882	7	+/-10%
	T TD	$\frac{N}{mm^2}$	ASTM D 882	7	+/-10%
CARICO DI ROTTURA , TENSILE STRENGTH ZUGFESTIFKEIT , CHARGE A LA RUPTURE	L MD	$\frac{N}{mm^2}$	ASTM D 882	40	+/-10%
	T TD	$\frac{N}{mm^2}$	ASTM D 882	24	+/-10%
ALLUNGAMENTO ALLA ROTTURA , REISSDEHNUNG ULTIMATE ELONGATION , ALLONGEMENT A LA RUPTURE	L MD	%	ASTM D 882	530	+/-50
	T TD	%	ASTM D 882	740	+/-50
PRESTIRO		%		> 150	