

FICHE TECHNIQUE

Référence : FIT421400

Désignation : Film pour système Fill Teck 400

# FillTeck™ Standard Lite

Film

| <u>Properties</u> | <u>Unit</u> | <u>Value</u> | <u>Tolerance</u> |
|-------------------|-------------|--------------|------------------|
| Raw Material      | –           | HDPE COEX    | –                |
| Custom Width      | mm          | 420          | ± 3              |
| Thickness         | μ           | 30           | ± 3%*            |
| Density @ 23°C    | g/cm³       | 0.942        | ± 0.5%           |
| Melting Point     | °C          | 126          | ± 3%             |
| Tensile Strength  | Mpa         | 34/39        |                  |

\*On average thickness

This information corresponds with our current level of knowledge and its purpose is to provide you with information regarding our products and their possible use. Therefore it makes no attempt to guarantee specific properties of the products or their suitability for particular applications.

The possible presence of intellectual property rights should be ascertained.

We guarantee the quality of our products within the limits defined in our General Conditions of Sale.