



Technical Data Sheet

Date: 08/04/10

Product : Standard transparent and black films, 20 - 35 μm

Technical Data :

Colour	:	transparent and black		
Elastic modulus MD	:	340	N/mm ²	(ASTM D882)
Elastic modulus CD	:	370	N/mm ²	(ASTM D882)
Tensile strength MD	:	27	N/mm ²	(ASTM D882)
Tensile strength CD	:	21	N/mm ²	(ASTM D882)
Elongation at break MD	:	150	%	(ASTM D882)
Elongation at break CD	:	550	%	(ASTM D882)
Tear resistance Elmendorf MD	:	24	N/mm	(ASTM D1922)
Tear resistance Elmendorf CD	:	80	N/mm	(ASTM D1922)
Impact strength Energy	:	25	J/mm	(OP intern WPC-020)



16, rue de l'Etang • Paris Nord 2 • 95977 ROISSY CDG Cedex

Services Commerciaux : tél. 3912* ou 0820 306 306* du lundi au vendredi de 8h à 18h30 - fax 0820 306 307* - www.raja.fr - Vos commandes 24h/24, 7 jours/7

Services Administratifs : tél. 01 48 17 30 00 du lundi au vendredi de 8h30 à 18h30 - fax 01 48 17 30 30.
* 0,099 € HT/min

RAJA S.A. au capital de 10 000 000 € RCS Bobigny B 937 080 414

